



## ANCHOR BOND® C.R.U. URETHANE (PIGMENTED)

### PRODUCT DESCRIPTION:

Anchor Bond® Chemical Resistant Urethane is a two-component acrylic/aliphatic polyurethane floor sealer that exhibits excellent characteristics for abrasion resistance, chemical resistance, flexibility, weathering and UV stability.

### RECOMMENDED FOR:

- ▶ Auto service centers
- ▶ Warehouses
- ▶ Computer rooms
- ▶ Laboratories
- ▶ Aircraft hangers
- ▶ Cafeterias
- ▶ Exterior tanks
- ▶ Indoor service & chemical exposure areas
- ▶ Outdoor service & chemical exposure areas

### SUBSTRATE:

Typically used as a topcoat over most Anchor Bond® Floor Systems that are exposed to extreme UV conditions and direct chemical contact.

### SOLIDS BY WEIGHT:

54%

### COLORS AVAILABLE:

White, off white, light gray, medium gray, dark gray, charcoal gray, tile red, brown, tan, beige, light blue, blue, green and clear.

### FINISH CHARACTERISTICS:

High Gloss (80-100 at 60° @ Erichsen glossmeter)

### MIX RATIO:

4 parts A / 1 part B

### RECOMMENDED THICKNESS / YIELD:

267 sq. ft / gallon @ 6 wet mils thickness

### PACKAGING INFORMATION:

5 gal kit

### STORAGE CONDITIONS:

Store all components in a dry area at a temperature of between 60 and 90°F. Avoid excessive heat and do not freeze.

### SHELF LIFE:

One (1) year in original, unopened container.

### CHEMICAL RESISTANCE DATA

REAGENT	RATING
acetic acid 5%	C
xylene	E
mek	B
methyl alcohol	B
gasoline	D
10% sodium hydroxide	E
50% sodium hydroxide	D
10% sulfuric acid	D
10% hydrochloric acid	D
20% nitric acid	C
ethylene glycol	D

Rating key:

- A – not recommended
- B – 2 hour term splash spill
- C – 8 hour term splash spill
- D – 72 hour immersion
- E – long-term immersion

### PRIMER:

Recommend Anchor Bond® W.B. Epoxy Prime/Seal (Clear). This product can be utilized as a topcoat on many other Anchor Bond® products. It can also be used as underlayments such as: Anchor Crete® SL, Anchor Crete® ¼", Anchor Bond® W.B. Epoxy or Anchor Bond® 100% Solids Epoxy Topcoat.

### TOPCOAT:

None recommended.

### CURE SCHEDULE:

Pot life (1 ½ gallon volume)	3-5 hours @ 70°F
Tack free (dry to touch)	2-4 hours @ 70°F
Recoat or topcoat	4-8 hours @ 70°F
Light foot traffic	14-24 hours @ 70°F
Full cure (heavy traffic)	3-5 days @ 70°F

## **ANCHOR BOND® C.R.U. URETHANE (PIGMENTED) MIXING AND APPLICATION INSTRUCTIONS**

### **1) PRODUCT STORAGE:**

Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 90°F.

### **2) SURFACE PREPARATION:**

Surface preparation will vary according to the type of complete system to be applied. For a one or two coat thin build system (3-10 mils dry) we recommend either mechanical scarification or acid etching until a suitable profile is achieved. For a complete system build higher than 10 mils dry, we recommend a fine brush blast (shot blast). All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'x4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.

### **3) PRODUCT MIXING:**

This product is 4 Parts A to 1 Part B mix ratio. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. Avoid whipping air into the coating.

### **4) PRODUCT APPLICATION:**

The mixed material can be applied by brush, roller or spray. Spraying may require extra safety precautions, therefore, read the MSDS before spraying. Maintain temperatures within the recommended ranges during the application and curing process. Properly prime the substrate. It is best to maintain a wet edge to avoid roller marks. Direct sunlight or high temperatures may cause visible roller marking during application.

### **5) RECOAT OR TOPCOATING:**

Multiple coats of this product are acceptable. If you opt to recoat this product, you must first be sure that all of the solvents have evaporated from the coating during the curing process. The information on the front side are reliable guidelines to follow. However, it is best to test the coating before recoating or topcoating. This can be done by pressing on the coating with your thumb to verify that no fingerprint impression is left. If no impression is created, then the recoat can be started. Always remember that colder temperatures will require more cure time for the product before recoating can commence. Before recoating or topcoating, check the coating to insure no contaminants exist. If a bluish or contaminants are present on a previous coat, remove with a standard detergent cleaner. When recoating this product with subsequent coats of the urethane, it is advisable to apply the recoat before 24 hours pass. Also, it is advisable to degloss the previous coat to insure a trouble free bond.

### **6) CLEANUP:**

Use ketone solvents

### **7) FLOOR CLEANING:**

Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

### **8) RESTRICTIONS:**

Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.

### **NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY**

We warrant that our product is manufactured to the specifications as stated here or in other publications. All other information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABILITY OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Uncured epoxy resins, polymers and their curing agents may be ALKALINE, TOXIC OR BOTH, DEPENDING ON THE PARTICULAR SYSTEM. THEY MAY CAUSE ALLERGIC REACTIONS OR HYPERSENSITIVITY REACTIONS. BEFORE USING ANY MATERIAL, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.